

CLUEDO Nm 9500

- **Composizione:** 76%WP/Alpacafine
24%PA/Poliamide (R.C.S VALIDO SOLO PER NYLON BIANCO E NERO)
- **Impiego e consigli:** 1 capo rett.fin.7
- **Tintura e cotte ottimali :** tutti i quantitativi, minimo 30 Kg con supplementi fino a 60 Kg
- **Solidità colori:** lavaggio 3/4 luce 4 secco 4
ATTENZIONE : PER NYLON R.C.S CONTATTARE IN FASE DI CAMPIONATURA/ORDINE IL REPARTO COMMERCIALE , IL QUALE VI INDICHERA' IL MINIMO DI PRODUZIONE E PREZZO.
- **Attenzioni specifiche :** La presenza sporadica di fibre scure naturali visibili su colori molto chiari e di fibre chiare visibili su colori molto scuri, è una caratteristica non eliminabile della fibra dell'alpaca in natura.In caso di riparaffinatura del filato, consigliamo di regolare le roccatrici a bassa velocità, per ottenere rocche morbide con densità uniforme.
L'effetto coloristico di questo articolo è stato ottenuto con metodi artigianali, pertanto piccole differenze di tonalità possono presentarsi sui capi in maniera casuale e questo è da considerarsi caratteristica e non difetto del prodotto.
- **Istruzioni di lavaggio:** Per mantenere un buon livello di pilling ed una mano morbida e gonfia, si consiglia di lavare i capi sul rovescio con acqua a 30 °C ed ammorbidente siliconico. Lasciare per 4-5 minuti fermi in ammollo. Poi circa 15 minuti suddivisi in delicata azione meccanica e scarico finale con centrifuga. Asciugatura in tumbler con azione moderata a 50-60 °C per circa 15/20 minuti. Nei filati con alta percentuale di mohair o alpaca, si consiglia di effettuare un prelavaggio a 30 °C con saponi neutri per sgrassare le fibre.
- **Nobilizzazione ed istruzioni per la manutenzione dei capi:** Dopo la fase di lavaggio, i capi potrebbero subire un leggero assestamento dimensionale, ed un normale rientro, pertanto consigliamo di effettuare le dovute prove, prima di procedere alla completa tessitura dei capi.
Per ottenere una buona mano e la giusta stabilità dimensionale del manufatto è sufficiente un abbondante vaporizzo durante lo stiro, evitando l'uso del piano superiore affinché il tessuto non subisca schiacciamenti o chiazze indesiderate, oppure lavare a secco con i normali solventi che si trovano in commercio. Per il trattamento con acqua, suggeriamo di lavare delicatamente in acqua con sapone ed ammorbidente neutro, avendo cura di girare sul rovescio i capi prima di tale operazione. Si consiglia di asciugare a velocità ridotta avendo cura di non essiccare troppo i capi.
- **Percentuale di scarto lavorazione:** Considerare una percentuale del 5/6%. Non si accettano reclami o resi per un quantitativo di filato smacchinato superiore a 5 Kg per bagno.
- **Attenzioni particolari:** Si consiglia una fase di prestiro ai pannelli prima del lavaggio.
Questo filato è stato volutamente ideato affinché ogni singolo prodotto sia unico ed irripetibile, pertanto la sequenza dei colori è completamente casuale.
Si consiglia di lavorare ad un guidafile.

Il Filato rispetta tutti i parametri del regolamento REACH

- **Composition:** 76%WP/Finealpaca
24%PA/Polyamide (R.C.S VALID ONLY FOR BLACK AND WHITE NYLON)
- **Knitting Suggestion:** 1 end flat machine g.7
- **Dyeing process- Optimal dyelots :** Tops dyed – minimum 30 Kg with surcharges until 60 Kg
- **Colour fastness:** washing 3/4 light 4 dry 4
- **ATTENTION:** FOR NYLON R.C.S, PLEASE CONTACT THE COMMERCIAL DEPARTMENT DURING THE SAMPLING / ORDERING PHASE, WHICH WILL INDICATE THE MINIMUM PRODUCTION AND PRICE.
- **Warnings:** The sporadic presence of visible natural dark fibres on very light colours and of light fibres visible on very dark colours is a characteristic of the fiber of alpaca in natural colors.In the event of re-waxing the yarn, set the winders at a low speed, thus attaining soft and uniformly dense cones.
- The shades of this yarn have been realised with craftsman proceedings, therefore any possible slight difference of colour-shades must not be considered as defects but distinctive features of the product. **Washing Instruction (Method applied on our collection' swatches):** To keep a good pilling rate and a soft handfeel, we suggest to wash garments on the back side with water at 30 °C and siliconic softener. Keep them in the water for 4-5 minutes. Then around 15 minutes divided in a delicate mechanical action and final draining with centrifuge. Drying in tumbler (very light mechanical action) for 15-20 minutes at 50/60 °C. We suggest to apply a pre-washing at 30 °C with neutral soaps to these articles with high percentage of alpaca and mohair, in order to degrease the fibers. In case of striping or jacquard knitwear with strong and contrasting colours, we suggest only to dry clean wash.
- **Ennobling:** After washing process, the garment could have a slight dimensional adjustment and a light shrinkage, for this reason we suggest to make some tests before proceeding with complete weaving of the garments.
In order to obtain a soft hand and a correct product dimensional stability it is advisable, to steam strongly when ironing, avoiding the use of iron, so that the yarn does not get squashed nor make glossier "spots". Dry cleaning with the normal solvents in commerce, or delicately to wash it in lukewarm water, with soap and neutral softener, taking care to perform these processes on reverse side of the knitwear.
- **Wastage percentage:** We recommend to calculate a 4-5%. We do not accept claims or returns for quantities of knitted yarn higher the 5 Kg per lot.
- **Special instruction:** We Suggest to pre-iron the panels before washing.
This yarn has been intentionally develop in order that every single product will be unique and unrepeatable, thus the colors' sequence is completely random.
We suggested knitting the yarn with only one yarn-guide.

The yarn respect all the parameters of the rule REACH

Percentuale media di condizionatura/Conditioning rate: 4,70/5,20%
Tariffa doganale / Custom Code : 51082090
Peso al metro quadro /Weight per square meter : 200 gr/mq – 200 gsm
Simboli di manutenzione/Washing symbols :



simboli lavaggio per colori uniti/care instruction for solid colours