

SEXY Nm 4/100.000

- **Composizione:** 49%WO/ EXTRAFINE MERINOS WOOL SUPER WASH (RWS ON DEMAND) 49%PVA-ALCOOL POLIVINILICO 2%PL/SEQUIN
 - **Composizione dopo il lavaggio** 98%WO EXTRAFINE MERINOS WOOL SUPER WASH (RWS ON DEMAND) 2%PL/SEQUIN
 - **Impiego e consigli:** 1 capo rett.fin.12-14
 - **Tintura / cotte ottimali :** Tinto TOPS – tutti colori stock service
 - **Solidità colori:** lavaggio 3/4 luce 4 secco 4
- Per i colori di particolare intensità e brillantezza le solidità possono variare.
- Attenzione specifiche:** Questo filato detiene una bella sofficità, in quanto il 50% circa del filato si scioglie al primo lavaggio, lasciando quindi spazio alle fibre di aprirsi e rigonfiare per conferire al manufatto un aspetto molto morbido e soffice. Questo si ottiene con un lavaggio delicato in acqua a 50°C per 6 minuti con sapone neutro, (se la temperatura raggiunge i 60°C la fibra si scioglierà meglio) avendo cura di risciacquare bene i capi (è importante utilizzare molta acqua per facilitare il dissolvimento del Solvron).
- Dopo la fase di lavaggio i capi potrebbero subire un leggero assestamento dimensionale, pertanto consigliamo di effettuare le dovute prove, prima di procedere alla completa tessitura dei capi. Vista la caratteristica del filato, si consiglia di tessere a velocità moderata prestando attenzione alla realizzazione del manufatto.
- Attenzioni particolari: Prima del lavaggio e dello scioglimento della percentuale di PVA, NON stirare e non lasciare i capi esposti a fonti di calore, questo andrebbe a compromettere il PVA, il quale successivamente non si scioglierà durante il lavaggio.
- Istruzioni di lavaggio:** Per mantenere un buon livello di pilling ed una mano morbida e gonfia, si consiglia di lavare i capi sul rovescio con acqua a 50 °C ammorbidente siliconico e sapone neutro. Lasciare per 4-5 minuti fermi in ammollo. Poi circa 15 minuti suddivisi in delicata azione meccanica e scarico finale con centrifuga. Asciugatura in tumbler con azione moderata a 50-60 °C per circa 10/15 minuti. In caso di maglieria rigata o jacquard con tinte forti e contrastanti, consigliamo di lavare il capo solo a secco.
- **Nobilizzazione ed istruzioni per la manutenzione dei capi:** Per ottenere una buona mano e la giusta stabilità dimensionale del manufatto è sufficiente un abbondante vaporizzo durante lo stiro, evitando l'uso del piano superiore affinché il tessuto non subisca schiacciamenti o chiazze indesiderate, oppure lavare a secco con i normali solventi che si trovano in commercio. Per il trattamento con acqua, suggeriamo di lavare delicatamente in acqua con sapone ed ammorbidente neutro, avendo cura di girare sul rovescio i capi prima di tale operazione. Si consiglia di asciugare a velocità ridotta avendo cura di non essiccare troppo i capi.
 - **Percentuale di scarto lavorazione:** Considerare una percentuale del 5-6%. Non si accettano reclami o resi per un quantitativo di filato smacchinato superiore a 5 Kg per bagno.
 - **Attenzione specifiche: Il manufatto deve essere lavorato a due o più guidafilati. Per mancata osservanza di queste istruzioni, non sarà preso in considerazione nessun tipo di reclamo.**
 - **Testare attentamente il filato in fase di campionatura, Pinori filati non sarà responsabile di alcun problema produttivo riscontrato in questa fase.**
 - **Raccomandiamo di controllare attentamente i teli durante il processo di tessitura e di interrompere immediatamente la lavorazione in caso di evidenti irregolarità o barrature di colore.**

Il Filato rispetta tutti i parametri del regolamento REACH

- **Composition:** 49%WO/WOOL EXTRAFINE MERINOS SUPER WASH (RWS ON DEMAND) 49%PL-PVA/ POLIVINILIC ALCOOL 2%PL/POLYESTER SEQUIN
 - **Composition after washing:** 98%WO EXTRAFINE MERINOS WOOL SUPER WASH (RWS ON DEMAND) 2%PL SEQUIN
 - **Knitting Suggestion:** 1 end flat machine g.12-14
 - **Dyeing process/ Optimal dyelots :** Top -dyed – all colour stock service
 - **Colour fastness:** washing 3/4 light 4 dry 4
- For especially brilliant and intense colours, colour fastness may vary.
- Special Attention:** This yarn has a nice softness, as approximately 50% of the yarn melts at the first wash, this fact makes the fibres free to open, swell to give the product a very soft and fluffy appearance. This is achieved by delicately washing in water at 50°C for 6 minutes with neutral soap (if the temperature reaches at60°C the fiber will melt better) , taking care to rinse the items well. (it is important to use plenty of water to facilitate the dissolution of the Solvron).
- After the washing phase, the garments may undergo a slight dimensional adjustment, therefore we recommend carrying out the necessary tests before proceeding with the complete weaving of the garments. Given the characteristics of the yarn, we recommend weaving at a moderate speed, paying attention to the creation of the product.
- Special attention:** Before washing and dissolving the percentage of PVA, absolutely DO NOT iron the item, and do not leave item exposed to a heat source, this would compromise the PVA, which will subsequently not dissolve during washing.
- Washing instructions:** To maintain a good level of pilling and a soft, swollen hand, we recommend washing the garments inside out with water at 50°C and silicon softener. Leave to soak for 4-5 minutes. Then about 15 minutes divided into delicate mechanical action and final drain with centrifuge. Drying in a tumbler with moderate action at 50-60 °C for approximately 10/15 minutes. In the case of striped or jacquard knitwear with strong and contrasting colours, we recommend dry cleaning only.
- Finishing and instructions for the maintenance of the garments:** To obtain a good feel and the right dimensional stability of the article, abundant steaming during ironing is sufficient, avoiding the use of the upper surface so that the fabric does not suffer crushing or unwanted staining, or washing dry with normal solvents found on the market. For treatment with water, we suggest washing delicately in water with soap and neutral fabric softener, taking care to turn the garments inside out before this operation. We recommend drying at a reduced speed, taking care not to overdry the items.
- **Wastage percentage:** We recommend to calculate a 5-6%. We do not accept claims or returns for quantities of knitted yarn higher the 5 Kg per lot.
 - **Warnings : Yarn must be knitted with 2 or more yarn-carriers (one carrier for each course/row of knitting). Pinori Filati SpA will not be responsible for any claim due to non-compliance of this instruction.**
 - **Please carefully test the yarn on sample order, Pinori Filati will not be responsible for any productions already encountered in this phase.**
 - **We recommend to carefully check the panels during knitting process and to stop immediately in case of defects or uneven colors.**

The yarn respect all the parameters of the rule REACH

Percentuale media di condizionatura/Conditioning rate: 3.00% 3,50%

Tariffa doganale / Custom Code : 55099100

Peso al metro quadro /Weight per square meter : 72 gr/mq – 72 gsm

Simboli di manutenzione/Washing symbols :



simboli lavaggio per colori uniti/care instruction for solid colours